

185 South Broad Street Pawcatuck, CT 06379 Phone: 860-599-5877 Fax: 860-599-5461

E-Mail: <u>customerservice@cablecomponents.com</u>

FluoroFoam® Masterbatch FEP	Technical Data Sheet	
CC301-26CM-51 3P	Date of Origin:	4/26/2016
	Latest Revision:	11/2/2021

**Description:** Masterbatch (MBC) FluoroFoam<sup>®</sup> FEP chemically foamable fluoropolymer pellets available for wire and cable insulation and jacketing material. FluoroFoam<sup>®</sup> MBC foamable pellets are

intended to be blended with FEP to achieve customer's desired expansion rate.

Material Property	Typical Values	Test Method
Dielectric Constant	2.1	ASTM D1531
Specific Gravity	2.20	ASTM D792
Melt Flow Rate (372 °C @ 5kg, g/10 min)	24-30	ASTM D1238
Melting Point (°C)	260	D.S.C
Limiting Oxygen Index (%)	>95	ASTM D2863
Operating Temperature (°C)	200	UL 444
REACH/RoHS Compliant	Directive 2002/95/EC RoHS/RoHS 2 Compliant	-
NFPA 70 National Electric Code Plenum References	NFPA 262 (UL 910) CSA FT6	-
UL Designation	UL Recognized Component Plenum Cable Compound (QMTM2.E324802)	-
Standard Packaging	Up to 998kg Gaylords or 91kg Drums	

ASTM Test methods are listed for reference only. Actual testing performed according to modified equipment and conditions. Specific test methods available upon request. The data presented here is intended for product selection purposes only. Typical properties represent data characteristics of the product, but do not necessarily reflect minimum values during normal testing. Please consult CCG Customer Service for detailed specifications.